



Test Report

No. 2128807/TY

Date : Nov 07 2006

Page 1 of 2

Report on the submitted sample said to be TPU VINYL - CLEAR.

SGS Job No. : 2206037
Application No. : OK6A12
Sample Receiving Date : NOV 01 2006
Testing Period : NOV 01 - 06 2006

Test Requested : As specified by client, to test the submitted sample with reference to the requirements of Mattel CPI of QSOP 0006-3610 (Rev. M on Apr 5, 2006) - Plasticizers.

Test Method : As specified in Mattel CPI of QSOP 0006-3610 (Rev. M on Apr 5, 2006) - Plasticizers.
Analysis was performed by Gas Chromatography Mass Spectrometry.

Test Results : Please refer to next page.

Conclusion : When tested as specified, the submitted sample complies with the requirements stated in Mattel CPI of QSOP 0006-3610 (Rev. M on Apr 5, 2006) - Plasticizers.

Signed for and on behalf of
SGS Hong Kong Ltd.

Lai Ka Yan, Margaret
Assistant Operations Manager

This document is issued by the Company subject to its General Conditions of Service printed hereon or available on request and accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated, (a) the results shown in this document refer only to the sample(s) tested and (b) such sample(s) are retained for 90 days only. This document cannot be reproduced except in full, without prior approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law.



Test Report

No. 2128807/TY

Date : Nov 07 2006

Page 2 of 2

Test Results

Accessible Materials – Clause 2.1.3

<u>Test item</u>		<u>1</u>	<u>Detection Limit</u>
Bis-(2-ethylhexyl) phthalate	(DEHP)	ND	0.003 %
Dibutyl phthalate	(DBP)	ND	0.003 %
Benzylbutyl phthalate	(BBP)	ND	0.003 %
Dilisononyl phthalate	(DINP)	ND	0.01 %
Diisodecyl phthalate	(DIDP)	ND	0.01 %
Di-n-octyl phthalate	(DNOP)	ND	0.003 %
Total (DEHP + DBP + BBP + DINP + DIDP + DNOP)		< 0.05 %	--
		<u>Limit : 0.1000 %</u>	

<u>Test item</u>		<u>1</u>	<u>Detection Limit</u>
Dimethyl phthalate	(DMP)	ND	0.005%
Diethyl phthalate	(DEP)	ND	0.005%
Dipentyl phthalate	(DPP)	ND	0.005%
Dinonyl phthalate	(DNP)	ND	0.01%
Dicyclohexyl phthalate	(DCHP)	ND	0.005%
Di-n-hexyl phthalate	(DHP)	ND	0.005%
Diisobutyl phthalate	(DIBP)	ND	0.01%
Dipropyl phthalate	(DPrP)	ND	0.005%
Diisooctyl phthalate	(DIOP)	ND	0.01%
Total (DMP + DEP + DPP + DNP + DCHP + DHP + DIBP + DPrP + DIOP)		< 0.08 %	--
		<u>Limit : 0.1000 %</u>	

Sample Description :

1. Transparent Plastic

- Note : 1. ND = Not detected
2. % = percentage weight by weight

*** End of Report ***